

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
221B419	Fluropon SR	Bone white	0.48	0.65	0.85	54	N	Y
221B420	Fluropon SR	Frisco white	0.71	0.65	0.85	86	Y	Y
221B421	Fluropon SR	Oyster white	0.63	0.55	0.85	75	N	Y
222B954	Fluropon SR	Cadet Gray	0.27	0.35	0.85	26	N	Y
222B963	Fluropon SR	Castle gray	0.40	0.35	0.86	43	N	Y
223C344	Fluropon SR	Pueblo tan	0.52	0.55	0.85	59	N	Y
224B204	Fluropon SR	Banner red	0.39	0.23	0.85	42	N	Y
229Z1281M	Fluropon Classic SR	Classic Copper penny	0.44	0.35	0.86	49	N	Y
229Z1292M	Fluropon Classic II SR	Anodic Bronze	0.25	0.35	0.84	23	N	Y
229Z1294M	Fluropon Classic SR	Classic platinum	0.48	0.35	0.85	54	N	Y
229Z1306M	Fluropon Classic II SR	Classic II Anodic Clear	0.56	0.35	0.83	64	N	Y
229Z1307M	Fluropon Classic IISR	Classic II Anodic satin	0.42	0.35	0.80	44	N	Y
229ZZ1244M	Fluropon Classic II SR	Vancouver copper	0.31	0.35	0.81	29	N	Y
384A353	Fluropon SR	Brite Red	0.32	0.34	0.79	30	N	Y
384AA324	Fluropon SR	Scarlet Red	0.34	0.39	0.85	35	N	Y
431A582	Fluropon SR L/S	Regal White	0.66	0.66	0.87	80	Y	Y
431A617	Fluropon SR	Solar White	0.68	0.66	0.85	82	Y	Y
431A700	Fluropon SR	Egyptian White	0.54	0.53	0.85	62	N	Y
431A704	Fluropon SR	Artic White	0.56	0.55	0.84	65	N	Y
431A811	Fluropon SR	Linen White	0.72	0.71	0.84	87	Y	Y
431A844	Fluropon SR	Regal White	0.70	0.68	0.85	85	Y	Y
431A853	Fluropon SR	Birch White	0.64	0.65	0.85	76	N	Y
431A861	Fluropon SR	Sierra White	0.72	0.69	0.85	88	Y	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 1 of 1

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
431A862	Fluropon SR	Polar White	0.65	0.64	0.86	78	Y	Y
431A886	Fluropon SR	Regal White	0.68	0.67	0.86	82	Y	Y
431A893	Fluropon SR	Bone White	0.72	0.70	0.84	87	Y	Y
431A894	Fluropon SR	Stone White	0.60	0.56	0.86	71	N	Y
431A900	Fluropon SR	Snowdrift White	0.62	0.61	0.84	73	N	Y
431A937	Fluropon SR	White	0.63	0.55	0.86	75	N	Y
431A965	Fluropon SR	White	0.72	0.71	0.86	88	Y	Y
431A982	Fluropon SR	Off White	0.71	0.67	0.85	86	Y	Y
431B021	Fluropon SR	New Bone White	0.65	0.65	0.86	78	Y	Y
431B023	Fluropon SR	Coastal White	0.71	0.67	0.86	86	Y	Y
431B034	Fluropon SR	Stone White	0.61	0.61	0.85	72	N	Y
431B437	Fluropon SR	Bone White	0.71	0.71	0.85	86	Y	Y
431B843	Fluropon SR	Brite White	0.78	0.77	0.83	96	Y	Y
431A922	Fluropon SR	Driftwood	0.45	0.35	0.86	50	N	Y
431R236	Fluropon SR	Regal White	0.67	0.66	0.84	80	Y	Y
431R444	Fluropon SR	Regal White	0.70	0.67	0.86	85	Y	Y
431R453	Fluropon SR	Ascot White	0.69	0.65	0.85	83	Y	Y
431R454	Fluropon SR	Bone White LG	0.69	0.65	0.84	83	Y	Y
431R454	Fluropon SR	Bone White	0.69	0.65	0.84	83	Y	Y
431R801	Fluropon SR	Morton White	0.61	0.55	0.86	72	N	Y
431R976	Fluropon SR	Regal White	0.70	0.68	0.84	85	Y	Y
432A776	Fluropon SR	Tundra	0.34	0.34	0.85	35	N	Y
432A857	Fluropon SR	Granite	0.36	0.35	0.84	37	N	Y
432A945	Fluropon SR	Granite	0.37	0.35	0.88	40	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 2 of 2

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
432B085	Fluropon SR	Slate Gray	0.40	0.40	0.85	43	N	Y
432B127	Fluropon SR	Regal Gray	0.44	0.44	0.84	48	N	Y
432B161	Fluropon SR	Ash Gray	0.39	0.39	0.84	41	N	Y
432B174	Fluropon SR	Portland Stone	0.46	0.47	0.86	52	N	Y
432B180	Fluropon SR	City Scape	0.37	0.34	0.85	39	N	Y
432B198	Fluropon SR	Clay	0.33	0.32	0.85	34	N	Y
432B288	Fluropon SR	Portland Stone	0.50	0.35	0.86	57	N	Y
432B290	Fluropon SR	Slate Gray	0.26	0.25	0.85	24	N	Y
432B291	Fluropon SR	Stone Gray	0.41	0.35	0.86	45	N	Y
432B292	Fluropon SR	Yorktown	0.35	0.35	0.86	37	N	Y
432B316	Fluropon SR	Chromium Gray	0.48	0.44	0.85	54	N	Y
432B323	Fluropon SR	Light Gray	0.54	0.55	0.85	62	N	Y
432B339	Fluropon SR	Granite SR	0.33	0.33	0.85	34	N	Y
432R1020	Fluropon SR	Zinc Gray	0.35	0.35	0.86	37	N	Y
432R1021	Fluropon SR	Dove Gray	0.47	0.35	0.86	53	N	Y
432R1022	Fluropon SR	Charcoal Gray LG	0.41	0.35	0.85	44	N	Y
432R1022	Fluropon SR	Old Town Gray	0.41	0.35	0.85	44	N	Y
432R1057	Fluropon SR	Slate Gray	0.43	0.35	0.85	47	N	Y
432R1065	Fluropon SR	Charcoal	0.32	0.35	0.85	32	N	Y
432R1144	Fluropon SR	Slate Grey	0.37	0.35	0.86	39	N	Y
432R1147	Fluropon SR	Seamist	0.31	0.25	0.86	31	N	Y
432R1261	Fluropon SR	Dawn Gray	0.27	0.25	0.86	26	N	Y
432R1357	Fluropon SR	L/S Charcoal	0.31	0.35	0.86	31	N	Y
432R1361	Fluropon SR	L/S Slate Gray	0.27	0.35	0.86	26	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 3 of 3

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
432R1403AR	Fluropon Hardcoat SR	Volcanic Stone	0.29	0.25	0.86	29	N	Y
432R1430	Fluropon SR	Charcoal Gray	0.29	0.25	0.89	30	N	Y
432R1452	Fluropon SR	L/G Old Town Grey	0.40	0.35	0.85	43	N	Y
432R1535	Fluropon SR	Slate Gray	0.31	0.35	0.86	31	N	Y
432R1544	Fluropon SR	Yorktown	0.35	0.35	0.86	37	N	Y
432R1581	Fluropon SR	Silver	0.43	0.35	0.86	48	N	Y
432R1582	Fluropon SR	Charcoal	0.29	0.25	0.86	29	N	Y
432R1602	Fluropon SR	Quaker Grey	0.26	0.25	0.86	25	N	Y
432R1603	Fluropon SR	LG Old Town Grey	0.44	0.35	0.86	49	N	Y
432R1689	Fluropon SR	Chromiun Gray	0.56	0.35	0.86	65	N	Y
432R1690	Fluropon SR	Blue Gray	0.28	0.25	0.85	27	N	Y
432R313	Fluropon SR	Ash Gray	0.39	0.39	0.85	42	N	Y
432R315	Fluropon SR	Slate Gray	0.40	0.39	0.86	43	N	Y
432R499	Fluropon SR	Old Town Gray	0.26	0.26	0.86	25	N	Y
432R521	Fluropon SR	Charcoal Gray	0.27	0.26	0.85	26	N	Y
432R526	Fluropon SR	Yorktown Gray	0.36	0.35	0.86	38	N	Y
432R614	Fluropon SR	Musket Gray	0.33	0.31	0.85	34	N	Y
432R669	Fluropon SR	Slate Gray	0.36	0.33	0.84	37	N	Y
432R692	Fluropon SR	Musket Gray	0.32	0.31	0.84	32	N	Y
432R783	Fluropon SR	Old Town Gray	0.39	0.35	0.87	43	N	Y
432R792	Fluropon SR	Charcal Gray	0.29	0.28	0.84	28	N	Y
432T335	Fluropon SR	Pebble	0.27	0.35	0.89	28	N	Y
432TR1692	Flurothane SR	Zinc GRay	0.37	0.35	0.87	40	N	Y
433A735	Fluropon SR	Brownstone	0.38	0.38	0.85	40	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 4 of 4

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
433B173	Fluropon SR	Almonde	0.60	0.57	0.84	70	N	Y
433B246	Fluropon SR	Sandstone	0.54	0.54	0.86	63	N	Y
433B272	Fluropon SR	Sandstone	0.51	0.50	0.85	58	N	Y
433B293	Fluropon SR	Light Stone	0.50	0.50	0.87	57	N	Y
433B311	Fluropon SR	Sandcastle	0.51	0.55	0.85	58	N	Y
433B312	Fluropon SR	Shelburne	0.69	0.68	0.85	83	Y	Y
433B315	Fluropon SR	Parchment	0.54	0.53	0.86	63	N	Y
433B328	Fluropon SR	Rawhide	0.53	0.51	0.86	61	N	Y
433B330	Fluropon SR	Almond	0.57	0.56	0.86	67	N	Y
433B331	Fluropon SR	Burnt Almond	0.43	0.42	0.86	48	N	Y
433B360	Fluropon SR	Light Stone	0.52	0.51	0.85	59	N	Y
433B364	Fluropon SR	Sierra Gold	0.47	0.46	0.86	53	N	Y
433B365	Fluropon SR	Beige	0.40	0.39	0.86	43	N	Y
433B442	Fluropon SR	Ivory	0.67	0.65	0.87	81	N	Y
433B464	Fluropon SR	Herringbone	0.64	0.65	0.86	77	N	Y
433B465	Fluropon SR	Shelburne	0.66	0.42	0.86	79	Y	Y
433B465	Fluropon SR	Shelburne	0.66	0.42	0.86	79	Y	Y
433B493	Fluropon SR	Light Seawolf	0.39	0.40	0.86	42	N	Y
433B496	Fluropon SR	Sandstone	0.54	0.55	0.85	62	N	Y
433B516	Fluropon SR	Lee Ivory	0.64	0.62	0.85	76	N	Y
433B529	Fluropon SR	Limestone	0.56	0.55	0.84	65	N	Y
433B530	Fluropon SR	Surrey Beige	0.42	0.41	0.85	46	N	Y
433B565	Fluropon SR	Sierra Tan	0.35	0.34	0.86	37	N	Y
433C1114	Fluropon SR	Rock Tan	0.61	0.55	0.76	72	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 5 of 5

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
433C704	Fluropon SR	Rock Tan	0.62	0.55	0.86	74	N	Y
433R1125	Fluropon SR	Beige	0.40	0.31	0.85	43	N	Y
433R1126	Fluropon SR	Tan	0.51	0.42	0.85	58	N	Y
433R1127	Fluropon SR	Gold	0.50	0.55	0.86	57	N	Y
433R1153	Fluropon SR	Ivory	0.60	0.55	0.85	71	N	Y
433R1215	Fluropon SR	Lee Ivory	0.65	0.55	0.85	78	Y	Y
433R395	Fluropon SR	Parchment	0.53	0.42	0.85	61	N	Y
433R396	Fluropon SR	Almond LG	0.61	0.55	0.85	72	N	Y
433R396	Fluropon SR	Sandstone	0.61	0.55	0.85	72	N	Y
433R397	Fluropon SR	Rawhide	0.55	0.42	0.85	64	N	Y
433R398	Fluropon SR	Surrey Beige	0.48	0.42	0.86	54	N	Y
433R476	Fluropon SR	Surrey Beige	0.53	0.53	0.85	61	N	Y
433R482	Fluropon SR	Almond	0.61	0.60	0.87	73	N	Y
433R754	Fluropon SR	Buckskin	0.38	0.31	0.85	40	N	Y
434A619	Fluropon SR L/S	Terra Cotta	0.37	0.36	0.88	40	N	Y
434A764	Fluropon SR	Brick Red	0.29	0.29	0.87	29	N	Y
434A847	Fluropon SR	Terra Cotta	0.35	0.35	0.87	37	N	Y
434A950	Fluropon SR L/S	Colonial Rel	0.29	0.27	0.85	28	N	Y
434A985	Fluropon SR	Regal Red	0.36	0.36	0.83	37	N	Y
434A986	Fluropon SR	Banner Red	0.42	0.41	0.84	45	N	Y
434B007	Fluropon SR	Conch	0.69	0.55	0.85	83	Y	Y
434B017	Fluropon SR	Burgundy	0.25	0.23	0.85	23	N	Y
434B072	Fluropon SR	Colonial Red	0.25	0.24	0.86	24	N	Y
434B095	Fluropon SR L/S	Burgundy	0.25	0.25	0.87	24	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 6 of 6

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
434B099	Fluropon SR	Regal Red	0.47	0.45	0.82	52	N	Y
434B134	Fluropon SR	Colonial Red	0.27	0.23	0.85	26	N	Y
434B166	Fluropon SR	Terra Cotta	0.29	0.32	0.85	28	N	Y
434B204	Fluropon SR	Ruby Red	0.40	0.34	0.82	42	N	Y
434B264	Fluropon SR	Cool Brite Red	0.44	0.43	0.84	48	N	Y
434B956	Fluropon SR	Red	0.29	0.32	0.87	29	N	Y
434R1005	Fluropon SR	Patriot Red	0.46	0.34	0.86	52	N	Y
434R1059	Fluropon SR	Fireweed	0.34	0.23	0.85	35	N	Y
434R356	Fluropon SR	Colonial Red	0.33	0.29	0.85	34	N	Y
434R626	Fluropon SR	Terra Cotta LG	0.38	0.32	0.86	41	N	Y
434R626	Fluropon SR	Redwood	0.38	0.32	0.86	41	N	Y
434R637	Fluropon SR	Colonial Red	0.32	0.23	0.86	33	N	Y
434R706	Fluropon SR	Colonial Red LG	0.34	0.32	0.86	35	N	Y
434R746	Fluropon SR	Brandywine	0.26	0.23	0.88	26	N	Y
434R774	Fluropon SR	Boysenberry	0.27	0.25	0.86	26	N	Y
434R808	Fluropon SR	Brandywine	0.26	0.23	0.85	24	N	Y
434R814	Fluropon SR	Tile Red	0.34	0.23	0.86	35	N	Y
434R843	Fluropon SR	Brite Red	0.49	0.34	0.84	55	N	Y
434R863	Fluropon SR L/S	Colonial Red	0.34	0.23	0.86	35	N	Y
434R883AR	Fluropon Hardcoat SR	Terra Red	0.34	0.36	0.86	35	N	Y
434R930	Fluropon SR	Bright Red	0.44	0.34	0.85	49	N	Y
434R986	Fluropon SR L/G	Regal Red	0.28	0.23	0.85	27	N	Y
434RZ254	Fluropon SR	Colonial Red	0.35	0.32	0.86	37	N	Y
434RZ592	Fluropon SR	Colonial Red	0.30	0.23	0.86	30	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 7 of 7

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
434RZ996	Fluropon SR	Red	0.30	0.23	0.86	30	N	Y
434X308	Fluropon SR	Coronado Red	0.38	0.37	0.84	40	N	Y
434Z097	Fluropon SR	Red	0.33	0.32	0.85	34	N	Y
435AA874	Fluropon SR	Natural Patina	0.39	0.39	0.85	42	N	Y
435AA875	Fluropon SR	Spruce	0.28	0.29	0.86	27	N	Y
435B127	Fluropon SR	L/G Patina Green	0.28	0.32	0.86	27	N	Y
435B249	Fluropon SR	Marine Green	0.35	0.35	0.85	36	N	Y
435B310	Fluropon SR L/S	Evergreen	0.26	0.26	0.87	25	N	Y
435B411	Fluropon SR	Patina Green	0.29	0.28	0.87	29	N	Y
435B411	Fluropon SR	Patina Green	0.29	0.28	0.87	29	N	Y
435B425	Fluropon SR	Aged Copper	0.47	0.46	0.85	53	N	Y
435B447	Fluropon SR	Teal Patina	0.37	0.37	0.86	39	N	Y
435B573	Fluropon SR	Patina	0.50	0.48	0.86	57	N	Y
435B577	Fluropon SR	Char Green	0.27	0.26	0.84	25	N	Y
435B578	Fluropon SR	Teal Patina	0.38	0.39	0.85	40	N	Y
435B631	Fluropon SR	Moss	0.28	0.28	0.86	27	N	Y
435B641	Fluropon SR	Aged Copper	0.49	0.38	0.86	56	N	Y
435B705	Fluropon SR	Patina Green	0.26	0.28	0.88	26	N	Y
435C002	Fluropon SR	Patina	0.36	0.32	0.84	37	N	Y
435C504	Fluropon SR	Teal LG	0.34	0.32	0.86	35	N	Y
435R1018	Fluropon SR	Hartford Green	0.28	0.25	0.85	24	N	Y
435R1019	Fluropon SR	Classic Green	0.32	0.32	0.86	33	N	Y
435R1039	Fluropon SR	Hartford Green	0.30	0.25	0.85	30	N	Y
435R1059	Fluropon SR	Indy Green	0.30	0.32	0.85	30	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 8 of 8

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
435R1081	Fluropon SR	Turquoise	0.35	0.32	0.85	36	N	Y
435R1082	Fluropon SR	Green	0.28	0.25	0.85	27	N	Y
435R154	Fluropon SR	Hemlock Green	0.35	0.32	0.85	36	N	Y
435R202	Fluropon SR	Patina Green	0.41	0.32	0.84	44	N	Y
435R222	Fluropon SR	Evergreen	0.26	0.25	0.85	24	N	Y
435R250	Fluropon SR	Patina Green	0.46	0.32	0.85	51	N	Y
435R270	Fluropon SR	Wood Duck Teal	0.25	0.25	0.86	24	N	Y
435R326	Fluropon SR	Classic Green	0.27	0.25	0.86	26	N	Y
435R328	Fluropon SR	Hunter Green	0.35	0.25	0.86	37	N	Y
435R340	Fluropon SR	L/S Evergreen	0.25	0.25	0.85	23	N	Y
435R341	Fluropon SR	L/S Hartford Green	0.26	0.25	0.86	25	N	Y
435R348	Fluropon SR	L/G Patina Green	0.46	0.32	0.85	51	N	Y
435R434	Fluropon SR	L/G Felt Green	0.31	0.25	0.84	31	N	Y
435R441	Fluropon SR	Evergreen LG	0.30	0.25	0.85	30	N	Y
435R535	Fluropon SR	Forest Green	0.28	0.25	0.85	27	N	Y
435R536AR	Fluropon Hardcoat SR	Alpine Evergreen	0.27	0.25	0.85	26	N	Y
435R546	Fluropon SR	Teal	0.29	0.25	0.86	29	N	Y
435R561	Fluropon SR	Teal	0.29	0.31	0.89	30	N	Y
435R582	Fluropon SR	Teal	0.30	0.28	0.85	30	N	Y
435R600	Fluropon SR	Arcadia Green	0.34	0.33	0.88	36	N	Y
435R603	Fluropon SR	Forest Green	0.27	0.26	0.85	26	N	Y
435R764	Fluropon SR	Evergreen	0.27	0.26	0.86	26	N	Y
435R787	Fluropon SR	Hemlock Green	0.34	0.33	0.86	35	N	Y
435R792	Fluropon SR	Classic Green	0.27	0.26	0.83	25	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 9 of 9

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
435R826	Fluropon SR	Hartford Green	0.28	0.25	0.86	27	N	Y
435R878	Fluropon SR	Hemlock Green	0.32	0.29	0.86	33	N	Y
435RZ1020	Fluropon SR	L/G Jade Green	0.31	0.32	0.86	31	N	Y
435RZ1100	Fluropon SR	Evergreen	0.26	0.25	0.85	24	N	Y
435RZ263	Fluropon SR	Evergreen	0.26	0.25	0.84	24	N	Y
435RZ268	Fluropon SR	Hartford Green	0.25	0.25	0.85	23	N	Y
435RZ271	Fluropon SR	Hartford Green	0.27	0.26	0.85	26	N	Y
435RZ327	Fluropon SR	Everglade	0.33	0.32	0.86	34	N	Y
435RZ601	Fluropon SR	Hunter Green SE	0.29	0.25	0.85	28	N	Y
435RZ850	Fluropon SR	Jade Green	0.29	0.29	0.85	28	N	Y
435TR1127	Flurothane II SR	Evergreen	0.25	0.25	0.89	25	N	Y
435Z576	Fluropon SR	Green	0.33	0.32	0.85	34	N	Y
436B307	Fluropon SR	Regal Blue	0.26	0.25	0.85	24	N	Y
436B396	Fluropon SR	Aegean Blue	0.32	0.28	0.86	33	N	Y
436B397	Fluropon SR	Legacy Blue	0.35	0.32	0.86	37	N	Y
436R1030	Fluropon SR	Regal Blue	0.26	0.25	0.85	24	N	Y
436R1051	Fluropon SR	Slate Blue	0.28	0.28	0.85	27	N	Y
436R1052	Fluropon SR	Tahoe Blue	0.26	0.25	0.85	24	N	Y
436R1063	Fluropon SR	Regal Blue	0.26	0.25	0.86	25	N	Y
436R1094	Fluropon SR	Roman Blue	0.26	0.26	0.85	24	N	Y
436R1140	Fluropon SR	River Teal	0.27	0.25	0.86	26	N	Y
436R1141	Fluropon SR	Harbor Blue	0.28	0.25	0.86	27	N	Y
436R1148	Fluropon SR	Harbor Blue	0.30	0.25	0.86	30	N	Y
436R1303AR	Fluropon Hardcoat SR	Boreal Blue	0.27	0.32	0.86	26	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 10 of 10

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
436R1328	Fluropon SR	Regal Blue	0.28	0.25	0.89	29	N	U
436R1332	Fluropon SR	Tahoe Blue	0.30	0.25	0.85	30	N	Y
436R1340	Fluropon SR	Slate Blue LG	0.30	0.25	0.85	30	N	Y
436R1384	Fluropon SR	L/G Tahoe Blue	0.30	0.25	0.86	30	N	Y
436R1419	Fluropon SR	Legacy Blue	0.34	0.32	0.86	35	N	Y
436R1420	Fluropon SR	Aegean Blue	0.30	0.28	0.86	30	N	Y
436R1451	Fluropon SR	Blue	0.29	0.25	0.86	29	N	Y
436R413	Fluropon SR	Alpine Blue	0.32	0.31	0.85	32	N	Y
436R691	Fluropon SR	Slate Blue	0.29	0.28	0.85	28	N	Y
436RZ1100	Fluropon SR	Regal Blue	0.26	0.25	0.85	24	N	Y
436RZ1127	Fluropon SR	Gallery Blue	0.28	0.25	0.86	27	N	Y
436RZ1142	Fluropon SR	Pacific Blue	0.29	0.25	0.86	29	N	Y
436RZ1385	Fluropon SR	Regal Blue LG	0.30	0.25	0.85	30	N	Y
436RZ1407	Fluropon SR	River Teal	0.29	0.25	0.86	29	N	Y
436RZ1412	Fluropon SR	Ocean Blue	0.29	0.25	0.86	29	N	Y
436RZ1467	Fluropon SR	River Teal	0.29	0.25	0.86	29	N	Y
436RZ1468	Fluropon SR	Regal Blue	0.27	0.25	0.86	26	N	Y
436RZ1469	Fluropon SR	Marine	0.28	0.25	0.86	27	N	Y
436RZ1473	Fluropon SR	Royale Blue	0.29	0.25	0.87	29	N	Y
436Z469	Fluropon SR	Apothecary Blue	0.26	0.26	0.85	24	N	Y
437B409	Fluropon SR L/S	Slate Gray	0.32	0.33	0.86	33	N	Y
437B453	Fluropon SR	Sahara Tan	0.41	0.39	0.86	45	N	Y
437B471	Fluropon SR	Khaki	0.42	0.42	0.85	46	N	Y
437B472	Fluropon SR	Taupe	0.30	0.29	0.85	30	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
437B480	Fluropon SR	Sierra Tan	0.38	0.38	0.86	41	N	Y
437B502	Fluropon SR	Herringbone	0.63	0.63	0.86	75	N	Y
437B614	Fluropon SR	Brown	0.29	0.28	0.85	28	N	Y
437B632	Fluropon SR L/S	Seal Brown	0.30	0.32	0.86	30	N	Y
437C1254	Fluropon SR	Taupestone	0.27	0.31	0.86	26	N	Y
437R1000	Fluropon SR	L/G Midnight Bronze	0.30	0.25	0.85	30	N	Y
437R1044	Fluropon SR	Tudor Brown	0.32	0.25	0.86	33	N	Y
437R1045	Fluropon SR	Dark Bronze	0.30	0.25	0.86	30	N	Y
437R1046	Fluropon SR	Statuary Bronze	0.32	0.25	0.86	33	N	Y
437R1051	Fluropon SR	Cocoa Brown	0.31	0.25	0.85	31	N	Y
437R1070	Fluropon SR	Bronze	0.33	0.31	0.86	34	N	Y
437R1100	Fluropon SR	LG Midnight Bronze	0.27	0.25	0.86	26	N	Y
437R1103	Fluropon SR	Brown	0.27	0.25	0.86	26	N	Y
437R1147	Fluropon SR	Brown	0.29	0.25	0.88	30	N	Y
437R1154	Fluropon SR	Campbell Solar Brown	0.34	0.25	0.86	35	N	Y
437R225	Fluropon SR	Seal Brown	0.29	0.25	0.86	29	N	Y
437R254	Fluropon SR	Mansard Brown	0.29	0.28	0.85	28	N	Y
437R270	Fluropon SR	Spartan Bronze	0.31	0.25	0.85	31	N	Y
437R278	Fluropon SR	Antique Bronze	0.43	0.31	0.86	48	N	Y
437R279	Fluropon SR	Dark Bronze	0.27	0.25	0.85	26	N	Y
437R339	Fluropon SR	Terra Tone	0.33	0.31	0.86	34	N	Y
437R340	Fluropon SR	Tudor Brown	0.29	0.25	0.86	34	N	Y
437R351	Fluropon SR	Mansard Brown	0.27	0.25	0.86	26	N	Y
437R398	Fluropon SR	Medium Bronze LG	0.33	0.31	0.86	34	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 12 of 12

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
437R413	Fluropon SR	L/S Mansard Brown	0.31	0.25	0.85	31	N	Y
437R414	Fluropon SR	L/S Medium Bronze	0.28	0.25	0.86	27	N	Y
437R415	Fluropon SR	L/S Dark Bronze	0.26	0.25	0.85	24	N	Y
437R454	Fluropon SR	Midnight Bronze	0.29	0.25	0.85	28	N	Y
437R492	Fluropon SR	Regal Brown	0.26	0.25	0.86	25	N	Y
437R493	Fluropon SR	Driftwood Cream	0.29	0.25	0.87	29	N	Y
437R520	Fluropon SR	Dark Bronze LG	0.33	0.25	0.85	34	N	Y
437R527	Fluropon SR	Keawe Brown	0.29	0.25	0.86	29	N	Y
437R530	Fluropon SR	Patrician Bronze	0.26	0.22	0.86	25	N	Y
437R597AR	Fluropon Hardcoat SR	Caramel	0.27	0.25	0.86	26	N	Y
437R622	Fluropon SR	Dark Bronze	0.28	0.25	0.89	29	N	Y
437R640	Fluropon SR	Seal Brown	0.31	0.31	0.87	32	N	Y
437R641	Fluropon SR Low Sheen	Dark Bronze	0.26	0.25	0.85	24	N	Y
437R641	Fluropon SR L/S	Dark Bronze	0.26	0.25	0.85	24	N	Y
437R644	Fluropon SR	Dark Bronze	0.26	0.25	0.85	24	N	Y
437R645	Fluropon SR	Mansard Brown	0.30	0.29	0.85	30	N	Y
437R813	Fluropon SR	Patrician Bronze	0.27	0.25	0.86	26	N	Y
437R840	Fluropon SR	Tudor Brown	0.30	0.25	0.86	30	N	Y
437R842	Fluropon SR	Dark Bronze	0.29	0.29	0.84	28	N	Y
437R845	Fluropon SR	Statuary Bronze	0.27	0.25	0.86	26	N	Y
437R993	Fluropon SR	Military Bronze	0.30	0.28	0.87	31	N	Y
437R994	Fluropon SR	Dark Bronze	0.26	0.25	0.84	24	N	Y
438A383	Fluropon SR L/S	Antique Black	0.28	0.27	0.85	27	N	Y
438A421	Fluropon SR	Black	0.27	0.27	0.85	26	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 13 of 13

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
438R462	Fluropon SR	Matte Black	0.27	0.27	0.86	26	N	Y
438R579	Fluropon SR	Matte Black	0.29	0.27	0.83	27	N	Y
438R597	Fluropon SR	L/S Matte Black	0.25	0.27	0.87	24	N	Y
438R599	Fluropon SR	Matte Black	0.25	0.27	0.85	23	N	Y
438R616AR	Fluropon Hardcoat SR	Black Mica	0.26	0.25	0.86	25	N	Y
438R644	Fluropon SR	Ebony Black	0.30	0.27	0.85	30	N	Y
438R648	Fluropon SR	Matte Black	0.25	0.27	0.84	23	N	Y
439RZ063M	Fluropon Classic II SR	Copper Penny	0.43	0.42	0.83	46	N	Y
439RZ1541M	Fluropon Classic II SR	Silversmith	0.53	0.35	0.79	59	N	Y
439RZ1543M	Fluropon Classic II SR	Coppy Penny	0.48	0.35	0.84	54	N	Y
439RZ1563M	Fluropon Classic II SR	Weathered Zinc	0.33	0.35	0.84	33	N	Y
439RZ1571M	Fluropon Classic II SR	Champagne Bronze	0.44	0.35	0.78	46	N	Y
439RZ1803M	Fluropon Classic II SR	Dove Metallic	0.25	0.35	0.79	20	N	Y
439RZ1824M	Fluropon Classic SR	Medium Gray	0.36	0.35	0.85	38	N	Y
439RZ1825M	Fluropon Classic SR	Light Bronze	0.55	0.35	0.86	64	N	Y
439RZ1826M	Fluropon Classic SR	Champagne Gold	0.51	0.35	0.85	58	N	Y
439RZ1827M	Fluropon Classic SR	Bright Silver	0.57	0.35	0.81	65	N	Y
439RZ2133M	Fluropon Classic II SR	Gray Velvet	0.30	0.35	0.82	28	N	Y
439RZ2309M	Fluropon SR	Antique Patina	0.38	0.35	0.85	40	N	Y
439RZ2388M	Fluropon SR	Copper Penny	0.51	0.35	0.85	58	N	Y
439RZ2597M	Fluropon SR Classic II SR	Weathered Zinc	0.36	0.35	0.78	35	N	Y
439RZ2723M	Fluropon SR	Weathered Zinc	0.34	0.35	0.85	35	N	Y
439X350	Fluropon SR	Zinc	0.51	0.49	0.79	56	N	Y
439Z1686M	Fluropon SR	White Metallic	0.70	0.65	0.88	85	Y	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 14 of 14

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
439Z1941M	Fluropon Classic II SR	Special Copper	0.49	0.35	0.85	55	N	Y
439Z2479M	Fluropon Classic II SR	Titanium	0.47	0.35	0.85	53	N	Y
439Z363	Fluropon SR	Champagne	0.37	0.36	0.83	38	N	Y
439Z469	Fluropon SR	Apothecary Blue	0.26	0.26	0.85	24	N	Y
439Z607M	Fluropon Classic II SR	Classic Copper	0.42	0.35	0.84	45	N	Y
439Z608	Fluropon SR	Silver Metallic	0.59	0.60	0.80	68	N	Y
439Z611M	Fluropon SR	Cool Copper Penny	0.44	0.41	0.81	47	N	Y
439Z613M	Fluropon Classic II SR	Champagne Metallic	0.37	0.35	0.80	37	N	Y
439Z615M	Fluropon Classic II SR	Prewathered Galvalume	0.30	0.28	0.79	27	N	Y
439Z618M	Fluropon Classic II SR	Zinc	0.55	0.49	0.76	62	N	Y
439Z637M	Fluropon Classic II SR	Bright Copper	0.49	0.47	0.85	55	N	Y
439Z644	Fluropon SR	Antique Patina	0.29	0.30	0.87	29	N	Y
439Z720M	Fluropon Classic II SR	Weathered Galvalume	0.30	0.35	0.85	28	N	Y
439Z739M	Fluropon Classic II SR H/S	Champagne SR	0.50	0.35	0.78	54	N	Y
439ZZ041	Fluropon SR	Copper Penny	0.46	0.35	0.85	51	N	Y
439ZZ042	Fluropon Classic II SR	Stainless	0.41	0.40	0.81	43	N	Y
439ZZ087M	Fluropon Classic II SR	Platinum	0.53	0.42	0.82	60	N	Y
439ZZ096	Fluropon SR	Champagne Gold	0.48	0.48	0.85	54	N	Y
439ZZ098	Fluropon SR	Champagne Pearl	0.48	0.48	0.81	53	N	Y
439ZZ099M	Fluropon Classic II SR	Pewter	0.31	0.27	0.86	31	N	Y
439ZZ104	Fluropon SR	Rosalind Rose	0.34	0.35	0.88	36	N	Y
439ZZ110	Fluropon SR	Silver Gray	0.29	0.26	0.86	29	N	Y
439ZZ138M	Fluropon Classic II H/S SR	Copper Penny	0.42	0.42	0.82	45	N	Y
439ZZ183M	Fluropon Classic II SR	Silver Gray	0.29	0.35	0.87	29	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
439ZZ221M	Fluropon Classic II SR	Bright Silver	0.60	0.60	0.77	68	N	Y
439ZZ583M	Fluropon Classic II SR	Sandstone Metallic	0.47	0.46	0.80	51	N	Y
439ZZ584M	Fluropon Classic II SR	Silver Metal	0.55	0.53	0.79	62	N	Y
439ZZ593M	Fluropon Classic II SR	Copper Metallic	0.45	0.44	0.85	50	N	Y
451A340	Fluropon SR	Birch White	0.55	0.55	0.86	64	N	Y
451A382	Fluropon SR	Solar White	0.69	0.68	0.86	84	Y	Y
451B017	Fluropon SR	Solar White	0.74	0.67	0.85	90	Y	Y
451R808	Fluropon SR	Regal White	0.70	0.67	0.86	85	Y	Y
451R809	Fluropon SR	Egyptian White	0.63	0.55	0.86	75	N	Y
451R810	Fluropon SR	Arctic White	0.63	0.55	0.86	75	N	Y
451R813	Fluropon SR	Polar White	0.70	0.67	0.86	85	Y	Y
451R835	Fluropon SR	Regal White	0.72	0.68	0.86	88	Y	Y
451R836	Fluropon SR L/G	Solar White- HDG	0.70	0.67	0.86	85	Y	Y
451R838	Fluropon SR L/G	Solar White- Galvalume	0.75	0.67	0.87	92	Y	Y
452A360	Fluropon SR	Shell Gray	0.42	0.41	0.86	46	N	Y
452A361	Fluropon SR	Mesa Gray	0.25	0.25	0.87	24	N	Y
452R1583	Fluropon SR	Zinc Gray	0.36	0.35	0.87	39	N	Y
452R1584	Fluropon SR	Ash Gray	0.50	0.35	0.86	57	N	Y
452R1587	Fluropon SR	Old Town Gray	0.38	0.35	0.87	41	N	Y
452R1591	Fluropon SR	Regal Gray	0.55	0.55	0.86	64	N	Y
452R1633	Fluropon SR L/G	Shell Gray	0.54	0.35	0.87	63	N	Y
453A356	Fluropon SR	Country Wheat	0.51	0.50	0.86	58	N	Y
453A358	Fluropon SR	Sandalwood	0.34	0.34	0.84	35	N	Y
453R1154	Fluropon SR	Sierra Tan	0.50	0.42	0.87	57	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 16 of 16

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
453R1155	Fluropon SR	Classic Beige	0.51	0.42	0.86	58	N	Y
453R1159	Fluropon SR	Parchment	0.50	0.42	0.86	57	N	Y
453R1160	Fluropon SR	Country Wheat	0.60	0.55	0.86	71	N	Y
453R1228	Fluropon SR	Sandstone	0.60	0.55	0.86	71	N	Y
454R1000	Fluropon SR	Bright Red	0.44	0.34	0.86	49	N	Y
454R1016	Fluropon SR	Colonial Red	0.33	0.23	0.87	35	N	Y
454R1045	Fluropon SR	Retro Red	0.40	0.25	0.87	44	N	Y
454R1100	Fluropon SR	Terra Cotta	0.38	0.32	0.87	41	N	Y
455R004	Fluropon SR	Solar Green	0.25	0.27	0.85	23	N	Y
455R021	Fluropson SR L/S	FB Green	0.30	0.25	0.85	30	N	Y
455R1101	Fluropon SR L/G	Cool Forest Green	0.29	0.25	0.87	29	N	Y
455R1102	Fluropon SR	Hemlock Green	0.30	0.25	0.86	30	N	Y
455R1103	Fluropon SR	Leaf Green	0.29	0.25	0.86	29	N	Y
455R1112	Fluropon SR	Marine Green	0.41	0.32	0.86	45	N	Y
455R1116	Fluropon SR	Arcadian Green	0.41	0.32	0.87	45	N	Y
455R1133	Fluropon SR	Jade Green	0.30	0.25	0.87	31	N	Y
455R1135	Fluropon SR	Forest Green	0.28	0.25	0.87	28	N	Y
455R1140	Fluropon SR L/G	Tahoe Blue	0.25	0.25	0.87	24	N	Y
455R1168	Fluropon SR	Hemlock Green	0.35	0.32	0.86	37	N	Y
455R1198	Fluropon SR	Leaf Green	0.30	0.25	0.86	30	N	Y
455RZ1179	Fluropon SR	Evergreen	0.28	0.25	0.85	27	N	Y
456R1384	Fluropon SR	Cool Ocean Blue	0.30	0.25	0.86	30	N	Y
456R1460	Fluropon SR	Tahoe Blue	0.25	0.25	0.87	24	N	Y
456R1461	Fluropon SR	Regal Blue	0.26	0.25	0.87	25	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 17 of 17

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
456R1463	Fluropon SR	Aegean Blue	0.29	0.25	0.86	29	N	Y
456RZ1385	Fluropon SR L/G	Cool Regal Blue	0.30	0.25	0.85	30	N	Y
457R1089	Fluropon SR	Dark Bronze	0.34	0.25	0.87	36	N	Y
457R1094	Fluropon SR	Rustique	0.31	0.31	0.87	32	N	Y
457R1095	Fluropon SR	Desert Beige	0.57	0.42	0.86	53	N	Y
457R1124	Fluropon SR	Weathered Copper	0.36	0.31	0.86	38	N	Y
457R1138	Fluropon SR	Burnished Slate	0.29	0.25	0.86	29	N	Y
457R1164	Fluropon SR	Dark Bronze	0.29	0.22	0.85	28	N	Y
457R1172	Fluropon SR	Weathered Copper	0.32	0.22	0.85	32	N	Y
458R645	Fluropon SR L/G	Cool Matte Black	0.30	0.27	0.85	30	N	Y
458R651	Fluropon SR	Matte Black	0.25	0.27	0.86	24	N	Y
459RA2723M	Fluropon Classic II SR	Weathered Zinc	0.34	0.35	0.85	35	N	Y
459RZ2422M	Fluropon SR	Copper Penny	0.51	0.35	0.86	58	N	Y
459RZ2430M	Fluropon SR	Champagne	0.47	0.35	0.85	53	N	Y
459RZ2431M	Fluropon SR	Silver	0.53	0.35	0.79	59	N	Y
459RZ2760M	Fluropon Classic II	Hazel Metallic	0.44	0.35	0.87	47	N	Y
459RZ388M	Fluropon SR	Zactique II	0.35	0.35	0.84	36	N	Y
459Z384	Fluropon SR	Antique Patina	0.29	0.35	0.87	29	N	Y
459ZZ789M	Fluropon Classic II L/G	Cool Zinc Metallic	0.28	0.35	0.87	28	N	Y
459ZZ799M	Fluropon Classic II SR	Weathered Zinc	0.27	0.35	0.80	23	N	Y
PMW0864	Polyester SR	Cotton White	0.68	0.68	0.84	82	Y	Y
SPA0361X	WeatherX SR	Ash Gray	0.48	0.47	0.87	55	N	Y
SPA0365X	WeatherX SR	Pewter Gray	0.32	0.25	0.85	32	N	Y
SPA0372X	WeatherX SR	Silver	0.46	0.46	0.86	52	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 18 of 18

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
SPA0390XB	WeatherX SR	Regal Gray	0.53	0.35	0.85	61	N	Y
SPA0397X	WeatherX SR	Light Gray	0.42	0.36	0.87	47	N	Y
SPA0402X	WeatherX SR	Pewter Gray	0.40	0.35	0.87	44	N	Y
SPA0404X	WeatherX SR	Light Gray	0.37	0.35	0.86	39	N	Y
SPA0413X	WeatherX SR	Clay	0.38	0.38	0.85	40	N	Y
SPA0414X	WeatherX SR	Gray	0.41	0.37	0.85	44	N	Y
SPA0418X	WeatherX SR	Charcoal Gray	0.38	0.25	0.85	38	N	Y
SPA0450X	WeatherX SR	Ash Gray	0.47	0.35	0.85	53	N	Y
SPA0460X	WeatherX SR	Light Gray	0.31	0.35	0.87	32	N	Y
SPA0468X	WeatherX SR	Light Gray	0.35	0.35	0.86	37	N	Y
SPA0498X	WeatherX SR	Lt Grey	0.37	0.35	0.85	39	N	Y
SPA0534X	WeatherX SR	Quaker Gray	0.28	0.25	0.85	27	N	Y
SPA0546X	WeatherX SR	Charcoal Gray	0.27	0.25	0.85	26	N	Y
SPA0610X	WeatherX SR	Shadow Grey	0.29	0.25	0.85	29	N	Y
SPA0654X	WeatherX SR	Charcoal	0.35	0.25	0.86	37	N	Y
SPA0658X	WeatherX SR	Charcoal	0.30	0.25	0.84	29	N	Y
SPA0660X	WeatherX SR	Charcoal	0.38	0.25	0.86	41	N	Y
SPA0670X	WeatherX SR	Black	0.28	0.24	0.86	27	N	Y
SPA0679X	WeatherX SR	Dark Gray	0.38	0.25	0.86	41	N	Y
SPA0687X	WeatherX SR	Light Gray	0.33	0.32	0.86	34	N	Y
SPA0688X	WeatherX SR	Charcoal Gray	0.29	0.25	0.88	30	N	Y
SPA0706X	WeatherX SR	Charcoal	0.30	0.25	0.85	30	N	Y
SPA0710X	WeatherX SR	Dk Gray	0.31	0.25	0.85	31	N	Y
SPA0721X	WeatherX SR	Ash Gray	0.44	0.25	0.86	49	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
SPA0725XB	WeatherX SR	Ash Gray	0.47	0.35	0.86	53	N	Y
SPA0726X	WeatherX SR	Charcoal	0.29	0.25	0.86	29	N	Y
SPA0728XB	WeatherX SR	Old Town Gray	0.35	0.35	0.87	37	N	Y
SPA0729XB	WeatherX SR	Old Zinc Gray	0.34	0.35	0.84	35	N	Y
SPA0731XB	WeatherX SR	Ash Gray	0.47	0.35	0.84	52	N	Y
SPA0734X	WeatherX SR	Green	0.28	0.22	0.85	27	N	Y
SPA0737XB	WeatherX SR	Slate Gray	0.31	0.25	0.86	31	N	Y
SPA0757X	WeatherX SR	Charcoal	0.34	0.25	0.86	35	N	N
SPA0767X	WeatherX SR	Ash Grey	0.51	0.35	0.86	58	N	Y
SPA0769X	WeatherX SR	Light Gray	0.48	0.35	0.86	54	N	Y
SPA0773X	WeatherX SR	Zinc Grey	0.41	0.35	0.86	45	N	Y
SPB0386X	WeatherX SR	Desert Brown	0.27	0.27	0.87	27	N	Y
SPB0388X	WeatherX SR	Dark Brown	0.26	0.22	0.87	25	N	Y
SPB0399X	WeatherX SR	Light Brown	0.25	0.25	0.86	24	N	Y
SPB0417X	WeatherX SR	Earth Brown	0.27	0.27	0.86	26	N	Y
SPB0427X	WeatherX SR	Burnished Slate	0.34	0.22	0.85	35	N	Y
SPB0441X	WeatherX SR	Sierra Brown	0.25	0.25	0.85	23	N	Y
SPB0455X	WeatherX SR	Bronze	0.26	0.26	0.86	25	N	Y
SPB0490X	WeatherX SR	Burnished Slate	0.28	0.22	0.85	27	N	Y
SPB0491X	WeatherX SR	Cocoa Brown	0.28	0.22	0.85	27	N	Y
SPB0511X	WeatherX SR	Cocoa	0.27	0.22	0.85	26	N	Y
SPB0540X	WeatherX SR	Brown	0.29	0.22	0.85	28	N	Y
SPB0546X	WeatherX SR	Lt Brown	0.31	0.32	0.86	31	N	Y
SPB0547X	WeatherX SR	Earth Brown	0.30	0.22	0.86	30	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 20 of 20

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
SPB0548X	WeatherX SR	Antique Bronze	0.28	0.22	0.86	27	N	Y
SPB0549X	WeatherX SR	Dark Brown	0.29	0.22	0.86	29	N	Y
SPB6530X	WeatherX SR	Antique Bronze	0.29	0.22	0.83	27	N	Y
SPB6531X	WeatherX SR	Cocoa Brown	0.35	0.22	0.85	36	N	Y
SPB6537X	WeatherX SR	Terratone	0.32	0.32	0.86	33	N	Y
SPB6538X	WeatherX SR	Dark Brown	0.29	0.22	0.86	29	N	Y
SPB6548X	WeatherX SR	Medium Brown	0.35	0.32	0.85	36	N	Y
SPB6551X	WeatherX SR	Medium Bronze	0.26	0.22	0.86	25	N	Y
SPB6552X	WeatherX SR	Dark Bronze	0.34	0.22	0.86	35	N	Y
SPB6553X	WeatherX SR	Dark Brown	0.34	0.22	0.86	35	N	Y
SPB6554X	WeatherX SR	Desert Brown	0.29	0.32	0.86	29	N	Y
SPB6561X	WeatherX SR	Weathered Copper	0.39	0.32	0.86	42	N	Y
SPB6565X	WeatherX SR	Dark Brown	0.33	0.22	0.85	34	N	Y
SPB6566X	WeatherX SR	Med Brown	0.33	0.32	0.86	34	N	Y
SPB6567X	WeatherX SR	Dark Brown	0.33	0.22	0.86	34	N	Y
SPB6575X	WeatherX SR	Patrician Bronze	0.28	0.22	0.85	27	N	Y
SPB6581X	WeatherX SR	Burnished Slate	0.26	0.22	0.86	25	N	Y
SPB6583XB	WeatherX SR	Weathered Copper	0.34	0.25	0.87	36	N	Y
SPB6584XB	WeatherX SR	Classic Brown	0.29	0.31	0.86	29	N	Y
SPB6586X	WeatherX SR	Brown	0.32	0.22	0.86	33	N	Y
SPB6592XB	WeatherX SR	Chestnut Brown	0.30	0.25	0.87	31	N	Y
SPB6604X	WeatherX SR	Dark Brown	0.31	0.22	0.85	31	N	Y
SPB6629X	WeatherX SR	Dark Brown	0.30	0.22	0.86	30	N	Y
SPB6631X	WeatherX SR	Brown	0.30	0.22	0.87	31	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
SPB6633X	WeatherX SR	Bronze	0.26	0.22	0.84	24	N	Y
SPD0350X	Weather X SR	Ivory	0.66	0.65	0.85	79	Y	Y
SPD0403X	WeatherX SR	Light Stone	0.50	0.50	0.87	57	N	Y
SPD0405X	WeatherX SR	Tan	0.41	0.37	0.86	45	N	Y
SPD0406X	WeatherX SR	Taupe	0.38	0.38	0.87	41	N	Y
SPD0408X	WeatherX SR	Beige	0.41	0.36	0.86	45	N	Y
SPD0413X	WeatherX SR	Desert Sand	0.42	0.36	0.87	47	Y	Y
SPD0414X	WeatherX SR	Saddle Tan	0.48	0.47	0.87	55	N	Y
SPD0415X	WeatherX SR	Ivory	0.65	0.63	0.86	78	Y	Y
SPD0421X	WeatherX SR	Clay	0.42	0.36	0.86	46	N	Y
SPD0423X	WeatherX SR	Sahara Tan	0.42	0.36	0.87	47	N	Y
SPD0441XB	WeatherX SR	Sandstone	0.51	0.55	0.86	58	N	Y
SPD0443X	WeatherX SR	Ivory	0.64	0.53	0.84	76	N	Y
SPD0456X	WeatherX SR	Sierra Tan	0.42	0.36	0.84	45	N	Y
SPD0457	WeatherX SR	Clay	0.37	0.37	0.87	40	N	Y
SPD0460X	WeatherX SR	Lt Stone	0.52	0.53	0.86	60	N	Y
SPD0462X	WeatherX SR	Clay	0.41	0.32	0.87	45	N	Y
SPD0470X	WeatherX SR	Light Stone	0.54	0.50	0.85	62	N	Y
SPD0472X	WeatherX SR	Rawhide	0.46	0.36	0.84	51	N	Y
SPD0473X	WeatherX SR	Light Stone	0.54	0.36	0.87	63	N	Y
SPD0473X	WeatherX SR	Pebble Beige	0.60	0.53	0.87	71	N	Y
SPD0482X	WeatherX SR	Tan	0.45	0.36	0.86	50	N	Y
SPD0503X	WeatherX SR	Tan	0.42	0.43	0.87	47	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
SPD0505X	WeatherX SR	Hickory Moss	0.38	0.32	0.87	41	N	Y
SPD0506X	WeatherX SR	Ivory	0.60	0.53	0.88	71	N	Y
SPD0511X	WeatherX SR	Light Stone	0.52	0.53	0.86	60	N	Y
SPD0545X	WeatherX SR	Wheat	0.54	0.53	0.85	62	N	Y
SPD0558X	WeatherX SR	Hickory	0.41	0.36	0.86	45	N	Y
SPD0559X	WeatherX SR	Parchment	0.59	0.53	0.86	70	N	Y
SPD0607X	WeatherX SR	Beige	0.67	0.53	0.85	80	N	Y
SPD0632X	WeatherX SR	Clay	0.37	0.32	0.86	39	N	Y
SPD0743X	WeatherX SR	Stone	0.53	0.36	0.86	61	N	Y
SPD0744X	WeatherX SR	Hickory	0.41	0.32	0.85	44	N	Y
SPD0745X	WeatherX SR	Ivory	0.59	0.53	0.86	70	N	Y
SPD0746X	WeatherX SR	Parchment	0.58	0.53	0.86	68	N	Y
SPD0750X	WeatherX SR	Beige	0.44	0.32	0.86	49	N	Y
SPD0755X	WeatherX SR	Sandstone	0.52	0.35	0.85	59	N	Y
SPD0756X	WeatherX SR	Surrey Beige	0.43	0.36	0.85	47	N	Y
SPD0779X	WeatherX SR	Beige	0.37	0.32	0.85	39	N	Y
SPD0781X	WeatherX SR	Pinewood	0.46	0.53	0.86	52	N	Y
SPD0783X	WeatherX SR	Ivory	0.56	0.53	0.85	65	N	Y
SPD0786XB	WeatherX SR	Classic Beige	0.49	0.42	0.86	56	N	Y
SPD0789XB	WeatherX SR	Desert Beige	0.49	0.42	0.87	56	N	Y
SPD0790XB	WeatherX SR	Mocha Tan	0.46	0.31	0.85	31	N	Y
SPD0792XB	WeatherX SR	Tumbleweed	0.57	0.55	0.87	67	N	Y
SPD0793XB	WeatherX SR	Taupe	0.38	0.35	0.85	40	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
SPD0794XB	WeatherX SR	Lightstone	0.57	0.55	0.85	66	N	Y
SPD0795XB	WeatherX SR	Lightstone	0.56	0.55	0.83	64	N	Y
SPD0816X	WeatherX SR	Briarwood Tan	0.46	0.36	0.86	52	N	N
SPD0832X	WeatherX SR	Light Stone	0.59	0.53	0.86	70	N	Y
SPD0833X	WeatherX SR	Mocha Tan	0.51	0.36	0.86	58	N	Y
SPD0834X	WeatherX SR	Taupe	0.34	0.32	0.86	35	N	Y
SPD0835X	WeatherX SR	Carlsbad Canyon	0.42	0.32	0.86	46	N	Y
SPD0855X	Fluropon SR L/G	L/G Sandstone	0.49	0.53	0.86	56	N	Y
SPD0856X	Fluropon SR L/G	L/G Surrey Beige	0.41	0.36	0.86	45	N	Y
SPG0367X	WeatherX SR	Evergreen	0.28	0.22	0.84	27	N	Y
SPG0369X	WeatherX SR	Med Green	0.27	0.22	0.86	26	N	Y
SPG0373X	WeatherX SR	Colony Green	0.31	0.32	0.87	32	N	Y
SPG0375X	WeatherX SR	Colony Green	0.36	0.35	0.87	39	N	Y
SPG0425X	WeatherX SR	Fern Green	0.27	0.22	0.85	26	N	Y
SPG0426X	WeatherX SR	Evergreen	0.27	0.22	0.88	27	N	Y
SPG0433X	WeatherX SR	Patina Green	0.34	0.32	0.87	36	N	Y
SPG0457X	WeatherX SR	Patina Green	0.33	0.32	0.86	34	N	Y
SPG0463X	WeatherX SR	Evergreen	0.27	0.22	0.86	26	N	Y
SPG0472X	WeatherX SR	Patina Green	0.36	0.32	0.84	37	N	Y
SPG0482X	WeatherX SR	Evergreen	0.25	0.22	0.86	24	N	Y
SPG0517X	WeatherX SR	Hunter Green	0.34	0.35	0.85	35	N	Y
SPG0518X	WeatherX SR	Forest Green	0.35	0.32	0.86	37	N	Y
SPG0560X	WeatherX SR	Evergreen	0.33	0.32	0.84	33	N	Y
SPG0571X	WeatherX SR	Forest (Fern) Green	0.27	0.22	0.85	26	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 24 of 24

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
SPG0679X	WeatherX SR	Hartford Green	0.27	0.22	0.85	26	N	Y
SPG0684X	WeatherX SR	Kelly Green	0.36	0.32	0.85	38	N	Y
SPG0699X	WeatherX SR	Medium Green	0.35	0.32	0.86	37	N	Y
SPG0717X	WeatherX SR	FERN	0.27	0.22	0.86	26	N	Y
SPG0718X	WeatherX SR	Melchers Green	0.30	0.22	0.85	30	N	Y
SPG0720X	WeatherX SR	Forest Green	0.25	0.22	0.85	23	N	Y
SPG0729X	WeatherX SR	Forest Green	0.32	0.32	0.87	33	N	Y
SPG0730X	WeatherX SR	Evergreen	0.28	0.22	0.85	27	N	Y
SPG0734X	WeatherX SR	Teal	0.29	0.22	0.87	29	N	Y
SPG0737X	WeatherX SR	Emerald Green	0.31	0.22	0.86	31	N	Y
SPG0739XB	WeatherX SR	Everglade	0.33	0.32	0.87	35	N	Y
SPG0747XB	WeatherX SR	Tarrace Green	0.41	0.32	0.87	45	N	Y
SPG0751X	WeatherX SR	Green	0.28	0.22	0.85	27	N	Y
SPG0758XB	WeatherX SR	Denali Green	0.26	0.25	0.86	25	N	Y
SPG0759XB	WeatherX SR	Forest Green	0.27	0.25	0.86	26	N	Y
SPG0762XB	WeatherX SR	Cypress Green	0.28	0.25	0.87	28	N	Y
SPG0770X	WeatherX SR	Fern Green	0.26	0.22	0.86	25	N	Y
SPG0786X	WeatherX SR	Patina Green	0.34	0.32	0.86	35	N	Y
SPG0787X	WeatherX SR	Forest Green	0.27	0.22	0.85	26	N	Y
SPG0791X	WeatherX SR	Denali Green	0.29	0.22	0.86	29	N	Y
SPL0299X	WeatherX SR	Hawaiian Blue	0.25	0.20	0.86	24	N	Y
SPL0300X	WeatherX SR	Blue	0.25	0.25	0.86	24	N	Y
SPL0301X	WeatherX SR	Gallery Blue	0.29	0.30	0.86	29	N	Y
SPL0333X	WeatherX SR	Roman Blue	0.32	0.29	0.85	32	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
SPL0341X	WeatherX SR	Blue	0.35	0.30	0.85	36	N	Y
SPL0342X	WeatherX SR	Hawaiian Blue	0.32	0.30	0.85	32	N	Y
SPL0343X	WeatherX SR	Slate Blue	0.31	0.30	0.87	32	N	Y
SPL0399X	WeatherX SR	Caribbean Blue	0.26	0.30	0.87	25	N	Y
SPL0461X	WeatherX SR	Gallery Blue	0.27	0.25	0.85	26	N	Y
SPL0549X	WeatherX SR	Gallery Blue	0.29	0.25	0.86	29	N	Y
SPL0587X	WeatherX SR	Blue	0.29	0.30	0.86	29	N	Y
SPL0589X	WeatherX SR	Heron Blue	0.32	0.25	0.85	32	N	Y
SPL0592X	WeatherX SR	Royal Blue	0.29	0.22	0.86	29	N	Y
SPL0593X	WeatherX SR	Regal Blue	0.26	0.25	0.85	24	N	Y
SPL0603X	WeatherX SR	Slate Blue	0.30	0.22	0.86	30	N	Y
SPL0605XB	WeatherX SR	Tahoe Blue	0.30	0.25	0.83	29	N	Y
SPR0250X	WeatherX SR	Crimson Red	0.33	0.32	0.85	34	N	Y
SPR0251X	WeatherX SR	Burgundy	0.26	0.27	0.84	24	N	Y
SPR0269X	WeatherX SR	Burgundy	0.25	0.22	0.86	24	N	Y
SPR0271X	WeatherX SR	Patriot Red	0.33	0.35	0.86	34	N	Y
SPR0282X	WeatherX SR	Red	0.28	0.24	0.85	27	N	Y
SPR0283X	WeatherX SR	Red	0.32	0.31	0.84	32	N	Y
SPR0285X	WeatherX SR	Glossy Red	0.27	0.25	0.85	26	N	Y
SPR0286X	WeatherX SR	Barn Red (k)	0.28	0.25	0.86	27	N	Y
SPR0289X	WeatherX SR	Rustic Red	0.36	0.35	0.86	38	N	Y
SPR0291X	WeatherX SR	Brite Red	0.38	0.32	0.86	41	N	Y
SPR0293X	WeatherX SR	Autumn Red	0.35	0.32	0.85	36	N	Y
SPR0312X	WeatherX SR	Scarlet Red	0.37	0.32	0.85	39	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 26 of 26

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
SPR0322X	WeatherX SR	Barn Red	0.30	0.25	0.88	31	N	Y
SPR0333X	WeatherX SR	Scarlet Red	0.33	0.25	0.88	35	N	Y
SPR0356X	WeatherX SR	Brick Red	0.32	0.32	0.86	33	N	Y
SPR0362X	WeatherX SR	Brite Red	0.32	0.32	0.86	33	N	Y
SPR0368X	WeatherX SR	Brick Red	0.37	0.32	0.86	39	N	Y
SPR0369X	WeatherX SR	Burgundy	0.32	0.25	0.85	32	N	Y
SPR0391X	WeatherX SR	Country Red	0.43	0.32	0.86	48	N	Y
SPR0437X	WeatherX SR	Berry	0.33	0.25	0.83	27	N	Y
SPR0438X	WeatherX SR	Burgundy	0.26	0.25	0.86	25	N	Y
SPR0442X	WeatherX SR	Burgundy	0.32	0.25	0.85	32	N	Y
SPR0496X	WeatherX SR	Dark Red	0.29	0.25	0.87	29	N	Y
SPR0518X	WeatherX SR	Brandywine	0.29	0.25	0.86	29	N	Y
SPR0524X	WeatherX SR	Brite Red	0.48	0.32	0.86	54	N	Y
SPR0525X	WeatherX SR	Classic Burgundy	0.28	0.25	0.85	27	N	Y
SPR0557X	WeatherX SR	Red	0.30	0.25	0.86	30	N	Y
SPR0559X	WeatherX SR	Colonial Red	0.29	0.25	0.87	29	N	Y
SPR0561X	WeatherX SR	Brite Red	0.47	0.32	0.86	53	N	Y
SPR0564X	WeatherX SR	Burgundy	0.27	0.25	0.86	26	N	Y
SPR0565XB	WeatherX SR	Canyon Red	0.40	0.32	0.86	43	N	Y
SPR0566XB	WeatherX SR	Blackberry	0.27	0.23	0.87	27	N	Y
SPR0572X	WeatherX SR	Burgundy	0.27	0.25	0.86	26	N	Y
SPR0578XB	WeatherX SR	Patriot Red	0.43	0.34	0.87	48	N	Y
SPR0583XB	WeatherX SR	Rustic Red	0.35	0.32	0.85	36	N	Y
SPR0587X	WeatherX SR	Burgundy	0.27	0.25	0.86	26	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 27 of 27

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
SPR0590	SMP SR	Deep Rose	0.41	0.32	0.86	45	N	Y
SPW0055X	WeatherX SR	Crystal White	0.65	0.64	0.85	78	Y	Y
SPW0246X	WeatherX SR	High Gloss White	0.71	0.72	0.85	86	Y	Y
SPW0267X	WeatherX SR	White	0.65	0.64	0.86	78	Y	Y
SPW0272X	WeatherX SR	Polar White	0.60	0.59	0.85	71	N	Y
SPW0276X	WeatherX SR	Crystal White	0.59	0.56	0.85	69	N	Y
SPW0276XB	WeatherX SR	Polar White	0.59	0.55	0.85	69	N	Y
SPW0279X	WeatherX SR	Bone White	0.56	0.55	0.86	65	N	Y
SPW0283X	WeatherX SR	Regal White	0.64	0.64	0.85	76	N	Y
SPW0285X	WeatherX SR	Alamo White	0.64	0.62	0.85	76	N	Y
SPW0293X	WeatherX SR	Brilliant White	0.66	0.65	0.87	80	Y	Y
SPW0295X	WeatherX SR	Brite White	0.71	0.68	0.85	86	Y	Y
SPW0305X	WeatherX SR	White	0.62	0.60	0.86	74	N	Y
SPW0315X	WeatherX SR	White	0.57	0.53	0.85	66	N	Y
SPW0324X	WeatherX SR	Bone White	0.54	0.53	0.87	63	N	Y
SPW0343X	WeatherX SR	White	0.56	0.53	0.86	65	N	Y
SPW0344X	WeatherX SR	Brite White	0.60	0.64	0.85	71	N	Y
SPW0348X	WeatherX SR	Polar White	0.73	0.64	0.85	89	Y	Y
SPW0353X	WeatherX SR	USDA White	0.61	0.64	0.85	72	N	Y
SPW0362X	WeatherX SR	Polar White	0.70	0.68	0.85	85	Y	Y
SPW0433X	WeatherX SR	Midwest White	0.58	0.53	0.86	68	N	Y
SPW0440X	WeatherX SR	Bone White	0.62	0.53	0.86	74	N	Y
SPW0454X	WeatherX SR	Brite White	0.72	0.68	0.86	88	Y	Y
SPW0502X	WeatherX SR	Imperial White	0.65	0.64	0.85	78	Y	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 28 of 28

# Valspar SR Roof Products Listed with Energy Star 2010

Code Number	Model	Color	Initial SR	3-Year Actual Solar Reflectivity or Default SR	Initial Emittance	SRI	Low Slope	Steep Slope
SPW0578X	WeatherX SR	Driftwood	0.51	0.35	0.86	58	N	Y
SPW0595X	Weather X SR	Morton White	0.58	0.55	0.86	68	N	Y
SPW0600XB	WeatherX SR	Egyptian White	0.60	0.55	0.85	71	N	Y
SPW0601XB	WeatherX SR	Arctic White	0.62	0.55	0.85	73	N	Y
SPW0602XB	WeatherX SR	Surf White	0.59	0.55	0.86	70	N	Y
SPW0603XB	WeatherX SR	Winter White	0.70	0.67	0.86	85	Y	Y
SPW0604XB	WeatherX SR	Polar White	0.64	0.12	0.86	77	N	Y
SPW0620X	WeatherX SR	White White	0.65	0.64	0.86	78	Y	Y
SPW0630X	WeatherX SR	White	0.73	0.68	0.85	89	Y	Y
SPW0659X	Fluropon SR L/G	L/G Driftwood White	0.55	0.53	0.86	64	N	Y
SPY0116X	WeatherX SR	Gold	0.47	0.48	0.86	53	N	Y
SPY0118X	WeatherX SR	Aztec Gold	0.53	0.53	0.86	61	N	Y
SPY0124X	WeatherX SR	Gold	0.55	0.53	0.86	64	N	Y

For the most current list, please visit [www.energystar.gov](http://www.energystar.gov)



valspar

VAL392  
051028  
Page 29 of 29